



Laying the
groundwork
for your
aesthetics

Dedicated primers
from **GC**
for dental laboratory use

GC

Durable bonding to ceramics and composites



CERAMIC PRIMER II is a specialised priming agent for all aesthetic indirect restorations.

For the additional application or repair of **GRADIA PLUS** or when individualizing GRADIA PLUS with GRADIA PLUS Lustre Paint use CERAMIC PRIMER II to ensure a good adhesion.



Apply CERAMIC PRIMER II before characterising your **CERASMART270** restorations with **OPTIGLAZE color**. For more in-depth effects, a cut-back technique can also be used in combination with GRADIA PLUS.



CERAMIC PRIMER II is your preferred partner to guarantee a strong interface. All-ceramics can be characterised with GRADIA PLUS, including zirconia frameworks.

The hero for all your metal-based frameworks



METAL PRIMER Z is a one-step resin-to-metal bonding agent.

For a strong connection between the metal framework and any type of resin-based material such as acrylics and methacrylate composites. An easy-to-use and proven bonding agent!

Before covering your metal framework with GRADIA PLUS Opaque, METAL PRIMER Z is used to create a chemical connection.



Besides its specific indication for priming metal-based frameworks, METAL PRIMER Z can alternatively also be used to bond to zirconia frameworks.

The base for modifying dentures



GC Acrylic Primer increases the adhesion between light-curing composites and conventional acrylic resins used in dental laboratory procedures like the modification of denture teeth or denture base resins.



All-in-one solution for luting and repair



G-Multi PRIMER is used for the pretreatment of restorations before luting with G-CEM LinkForce or G-CEM Veneer and can also be used for intraoral repairs. It contains three different chemical agents to ensure a perfect adhesion to all types of restorations.



008551	CERAMIC PRIMER II, 3mL
009295	METAL PRIMER Z, 5ml
901138	GC Acrylic Primer, 6mL
009553	G-Multi PRIMER, 5 mL

CERAMIC PRIMER II, CERASMART270, GC Acrylic Primer, G-CEM LinkForce, G-CEM Veneer, GRADIA PLUS, METAL PRIMER Z and OPTIGLAZE color are trademarks of GC.

GC EUROPE N.V.
Head Office
Researchpark
Haasrode-Leuven 1240
Interleuvenlaan 33
B-3001 Leuven
Tel. +32.16.74.10.00
Fax. +32.16.40.48.32
info.gce@gc.dental
<http://www.gceurope.com>

GC UNITED KINGDOM Ltd.
Coopers Court
Newport Pagnell
UK-Bucks. MK16 8JS
Tel. +44.1908.218.999
Fax. +44.1908.218.900
info.uk@gc.dental
<http://uk.gceurope.com>

GC